ABS-FR-WT-285 ? Technical Datasheet

ABS Flame-Retardant ? White

Type: ABS

Diameter: 2.85mm

Density: 1.05 g/cm‡

Melting / print temp: 240-260℃

Nozzle temp: 240-260℃

Bed temp: 90-110℃

Tensile strength: 40-48 MPa

Elongation at break: 20-35 %

Hardness: Shore D 76

Spool weight: 1.0 kg

Certifications: ISO 9001, UL94-V0, RoHS

DEMO DOCUMENT ? replace with your own datasheet before launch.