PC-TR-CL-175 ? Technical Datasheet

PC Polycarbonate ? Clear

Type: PC

Diameter: 1.75mm

Density: 1.21 g/cm‡

Melting / print temp: 270-300℃

Nozzle temp: 270-300℃

Bed temp: 100-120℃

Tensile strength: 60-72 MPa

Elongation at break: 6-10 %

Hardness: Shore D 84

Spool weight: 1.0 kg

Certifications: ISO 9001, RoHS, REACH

DEMO DOCUMENT ? replace with your own datasheet before launch.