PLA-WD-OK-175 ? Technical Datasheet

Wood-fill PLA ? Oak

Type: PLA

Diameter: 1.75mm

Density: 1.28 g/cm‡

Melting / print temp: 195-215℃

Nozzle temp: 195-215℃

Bed temp: 45-55℃

Tensile strength: 38 MPa

Elongation at break: 5-8 %

Hardness: Shore D 72

Spool weight: 1.0 kg

Certifications: ISO 9001, FDA

DEMO DOCUMENT ? replace with your own datasheet before launch.